



ADHESIVE POLYESTER TAPE

1/1

06/07

A 7

1 - CONSTRUCTION

- Terephtalate of polyethylene film support 23 μ .
- Adhesive mass rubber thermosetting for reference 815.
- Adhesive mass acrylic for reference 507.
- Grade B 130° C. Printable.



2 - CHARACTERISTICS

SPECIFICATION	UNIT	R 815	R 507
Nature of support		Polyester	Polyester
Adhesive Mass		Rubber	Acrylic
Total Thickness	mm	0.05	0.05
Breaking Resistance	N/cm	35	35
Dielectric Strenght	Volt	4500	5000
Temperature Resistance	°C	130	130
Adhesive Strength on steel	N/cm	4.0	4.3
Breaking Elongation	%	80 \pm 20	80 \pm 20
Corrosion factor		0.95	1.00
Insulating Resistance	M Ω	1 x 10 ⁶	1 x 10 ⁶
Lifetime	Month	6	12
Colour		yellow	Translucent

3 - APPLICATIONS

- Insulation between layers. Holding threads coming out.
- Bobbins finishing. Binding of threads' parts.
- Insulation of bobbins.
- Maintain insulated products between layers.
- Protection of soldering and insulation of motors.

4 - PRESENTATION

- Standard widths :
9 - 12 - 15 - 19 - 25 - 30 - 38 - 50 mm.
6 for special demand.
- Meters per roll :
standard : 66 M on 76 mm cores.



We recommend to protect them from heat, humidity and at a temperature between + 10 and + 30°C, box standing up, roll flat .