



CETAVINYL[®] STANDARD SLEEVING

1/1

10/10

C 1

1 - CONSTRUCTION

- Polychloride Vinyl extruded sleeving "PVC".
- Very flexible sleeving and brilliant.



2 - CHARACTERISTICS

SPECIFICATION	R
- Temperature of use	- 20 + 80 °C
- Dielectric Strength	16 KV/mm
- Breaking Resistance	18 N/mm ²
- Breaking Elongation	320 %
- Density	1,25 g/cm ³
- Shore Hardness	82 Sh A

3 - APPLICATIONS

- Cabling, insulation, protection and marking.
- Electric motors, car industry.
- Domestic appliances industry, tool machines...



4 - PRESENTATION

- Conditioning : coils.
- Colours : crystal, white, yellow, orange, red, purple, blue, green, black, yellow/green.

DIAMETER mm	LENGTH per COIL	DIAMETER mm	LENGTH per COIL	DIAMETER mm	LENGTH per COIL	DIAMETER mm	LENGTH per COIL
0,5 x 1,2	500 M	4,0 x 5,0	500 M	12,0 x 13,1	12,0 x 13,1	22,0 x 24,0	50 M
1,0 x 1,8	500 M	5,0 x 5,8	500 M	13,0 x 14,2	13,0 x 14,2	24,0 x 26,0	50 M
1,5 x 2,3	500 M	5,0 x 6,0	500 M	14,0 x 15,2	14,0 x 15,2	25,0 x 27,0	50 M
2,0 x 2,7	500 M	6,0 x 6,9	400 M	15,0 x 16,2	15,0 x 16,2	26,0 x 28,0	25 M
2,0 x 3,0	500 M	7,0 x 8,0	250 M	15,0 x 21,0	15,0 x 21,0	28,0 x 30,0	25 M
2,5 x 3,3	500 M	8,0 x 9,0	250 M	16,0 x 17,3	16,0 x 17,3	30,0 x 32,0	25 M
3,0 x 3,8	500 M	9,0 x 10,0	200 M	18,0 x 19,5	18,0 x 19,5		
3,0 x 4,0	500 M	10,0 x 11,0	150 M	20,0 x 22,0	20,0 x 22,0		
3,5 x 4,3	500 M	11,0 x 12,0	150 M	20,0 x 26,0	20,0 x 26,0		
4,0 x 4,8	500 M						

We recommend to protect them from heat, humidity and at an ambient temperature.