



## EXTRUDED SILICONE SLEEVING

1/1

06/07

# C 4

### 1 - PROPERTIES

Material	Silicone
Shore Hardness	From 60 to 70 Sh A
Temperature of use	- 80 + 240 °C (Softness to be kept in low temperatures)
Chemical Properties	Good resistance to fluids (citric acid, alcohols, vegetal and animal oils)
Breaking Elongation	300 %
Density	1,20 g/cm <sup>3</sup>
Dielectric Strength	20 KV/mm
Breaking Strength	9,5 N/mm <sup>2</sup>

### 2 - CHARACTERISTICS

DIAMETER	LENGTH	DIAMETER	LENGTH
1 x 3	100 M	10 x 14	50 M
2 x 6	100 M	12 x 16	50 M
3 x 6	100 M	16 x 22	50 M
4 x 8	50 M	18 x 22	50 M
6 x 9	50 M	22 x 29	50 M
8 x 12	50 M	30 x 35	50 M

For other dimensions, please contact us

### 3 - APPLICATIONS

- Cabling - Mechanical and dielectric protection
- Motor industry - Electrical appliances - medical - food - electro technical industry.
- Good flexibility.

### 4 - PRESENTATION

- Coils : from 20 m to 100 m.
- Colours : Translucid (other colors are available).
- Diameters : Available from 1 to 35 mm.

