

1 - CONSTRUCTION

- Polychloride Vinyl extruded sleeving "PVC".
- Flexible sleeving and mat. (stiffer than the standard quality).



2 - CHARACTERISTICS

SPECIFICATION	HT
- Temperature of use	- 16 + 105 °C
- Dielectric Strength	16 KV/mm
- Breaking Resistance	18 N/mm ²
- Breaking Elongation	≥ 200 %
- Density	1,41 g/cm ³
- Shore Hardness	93 Sh A

- Good resistance to flame - self extinguishing
- Good resistance to hydrocarbons
- Good mechanical resistance

3 - APPLICATIONS

- Cabling, insulation, protection, marking.
- Electric motors, car industry (motor bonnets),
- Domestic appliances, tool machines.



4 - PRESENTATION

- Conditioning : coils.
- Colours : white, yellow, orange, red, purple, blue, green, black, yellow/green.

DIAMETER mm	LENGTH per COILS	DIAMETER mm	LENGTH per COILS	DIAMETER mm	LENGTH per COILS	DIAMETER mm	LENGTH per COILS
0,5 x 1,2	500 M	4,5 x 5,4	500 M	12,0 x 13,0	100 M	22,0 x 24,0	50 M
1,0 x 1,8	500 M	5,0 x 5,9	500 M	13,0 x 14,0	100 M	24,0 x 26,0	50 M
1,5 x 2,3	500 M	6,0 x 7,0	400 M	14,0 x 15,0	100 M		
2,0 x 2,8	500 M	7,0 x 8,0	250 M	15,0 x 16,2	50 M		
2,0 x 3,0	500 M	8,0 x 9,0	250 M	16,0 x 17,3	50 M		
2,5 x 3,3	500 M	9,0 x 10,0	200 M	18,0 x 19,5	50 M		
3,0 x 3,8	500 M	10,0 x 11,0	150 M	20,0 x 22,0	50 M		
3,5 x 4,4	500 M	11,0 x 12,0	150 M				
4,0 x 4,9	500 M						

We recommend to protect them from heat, humidity and at an ambient temperature.