

1 - CONSTRUCTION

- Round and solid E glass yarn braid with tight stitches.
- 3 qualities :
 - UNBLEACHED : Textile ensimage.
 - A.S : The yarn is covered with an amino silane finish.
 - A.R.I : Acrylic impregnation to avoid fraying. Makes tying easier. Improves blocking of bindings. Best resistance to rubbing.



2 - CHARACTERISTICS

- UNBLEACHED AND A.S CORD				CLASS C
REFERENCE	DIAMETER - mm unbleached (- 0,2 + 0,3) ecru	WEIGHT per meter g/m (+ - 4%)	BREAKING RESISTANCE daN	LENGTH meter per bobbin
S 31	1	2,0	> 35	200 - 1000
S 32	1,5	3,6	> 75	600
S 33	2	6,0	> 115	100 - 500
S 34	3	8,0	> 155	150 - 500
S 35	4	11,0	> 190	500
S 36	5	33,0	> 300	250
S 37	6	39,0	> 500	200

- A.R.I CORD		(no fraying)	CLASS F
	ø varnished (- 0,2 + 0,3)		
S 31	1	2,0	> 40
S 32	1,5	3,6	> 85
S 33	2	6,0	> 130
S 34	3	8,0	> 180
S 35	4	11,0	> 215
S 36	5	33,0	> 345
S 37	6	39,0	> 575



3 - APPLICATION

- Bindings, bandings, fastenings.

4 - PRESENTATION

- Conditioning: jaws bobbins.
from ø 1 to 4 mm : plastic bobbins.
from ø 5 mm : cardboard bobbins.
- Colour : unbleached.
- Length per bobbin :
Standard: please refer to the chart above.
Others possibilities: please question us.



We recommend to protect them from dust, humidity, at an ambient temperature.