

### 1 - CONSTRUCTION

- Treated Bonded fibre (Fibranne).
- Adhesive mass : Thermosetting rubber for R1 and R13.
- Good resistance to traction for R145 and high flexibility and good adhesive mass, wich quaranty a good closing on non perfectly clean surfaces.



### 2 - CHARACTERISTICS

SPECIFICATION	UNIT		AT 121	R 145
Nature of support			Fibranne	Fibranne
Adhesive Mass			Rubber	Rubber
Total Thickness	mm		0.25	0.29
Breaking Resistance	N/cm		75	115
Dielectric strenght	Volt		800	1000
Temperature of use	°C		65 max	120 max
Adhesive Strenght on Steel	N/cm		3.5	3.5
Breaking Elongation	%		10	14
Lifetime	Month		6	6

### 3 - APPLICATIONS

- Bindings, beam of cable for automotive.
- Insulation of bobbins.
- Protection of pieces against rubbing.
- Closing of metallic box.

### 4 - PRESENTATION

- Standard widths :  
12 - 15 - 19 - 25 - 30 - 38 - 50 mm.
- Colours :  
R 1 : white - R 13 : black.  
R 145 : unbleached, black, grey, red, white.
- Meters per roll :  
standard : 50 M on 76 mm cores.  
for the ref. R 13 auto : 25 M on 38 mm cores



We recommend to protect the tape from heat humidity and at a temperature between + 10 and + 30°C, box up, roll flat.