

1 - CONSTRUCTION

- Tape made of para-aramid fibers type Kevlar® or Twaron®.
- Thermal class : H 200 °C.
- The tape is like a lace.
- Is slightly impregnated to avoid fraying out.



2 - CHARACTERISTICS

SPECIFICATION	UNIT	AR 26	AR 26	AR 26		
Width without tension	mm	8.0	12.0	20.0		
Width with tension	mm	7.9	11.8	19.8		
Weight	g/m	0.30	1.93	3.05		
Breaking Resistance	daN	> 50	> 75	> 150		
Breaking Elongation	%	2.0	2.5	3.0		
Shrinkage without tension	%	0.2 à 0.3	0.2 à 0.3	0.2 à 0.3		
Thickness	mm	0.35	0.35	0.35		

- The breaking elongation is 2/3 of resistance.
- The shrinkage period lasts 1 hour at 140 °C.

3 - APPLICATIONS

- All bindings requiring a high strength for motors and transformers.
- Good impregnation power.



4 - PRESENTATION

- Standard widths : refer to the chart above.
- other widths: please question us.
- Colour : Yellow.
- Conditioning : on rolls or on plastic jaws bobbins.

We recommend to protect them from dust, humidity, at an ambient temperature.